

TECHNICAL DATA

CALDE® MAG GUN S 75

PRODUCT TYPE	: Basic product
	Gunning mix
Maximum recommended temperature	: 1700°C
Main component	: Magnesia
Type of bond	: Chemical, Silicate
Appearance	: Dry, for addition of water
Packaging	: Sacks or big bags
Shelf life	: 9 months
Installation method	: Gunning
Maximum grain size	: 3.5 mm
Material required	: 1.95 t/m3 (Rebound excluded)
Drinking water required for mixing on site	: Added at the nozzle
Guidelines	: Installation Nr 26

PRODUCT PROPERTIES	STANDARD	AVERAGE VALUES	UNITS
CHEMICAL ANALYSIS			
MgO	EN ISO 1927-3	75.0	%
SiO2	EN ISO 1927-3	18.0	%
CaO	EN ISO 1927-3	4.5	%
Fe2O3	EN ISO 1927-3	1.3	%
Na2O	EN ISO 1927-3	0.6	%

Commercial Code : MBG70023Version : 10Date : 03/12/2018

The data are current production averages. They cannot be used as limits for a specification.