

PRODUCT DATA SHEET

BRSBENT SQ — ACTIVATED BENTONITE

Premium drilling fluid material for HDD, slurry TBM and deep foundation applications

Description

BRSBENT SQ is a versatile activated bentonite with strong thixotropic properties, ideal for all freshwater-based drilling systems. It suits slurry TBM, deep foundations, and HDD projects, with adjustable rheology for optimal performance in diverse drilling applications.

Main Functions

- Ensures borehole / trench stability
- Builds impermeable membrane / filter cake
- Promotes smooth circulation
- Facilitates efficient separation



Product Features

- ✓ For robust drilling fluid systems
- ✓ Good interaction with most SM additives
- ✓ Highly thixotropic with enhanced gel strengths
- ✓ Well-balanced rheology and predictability

Packaging

Small Bags	Jumbo Bags	Bulk Tanker
25 kg	1,000 kg · 1,200 kg · 1,400 kg	22 ± 2 MT

Storage

Keep the product in its original packaging at normal temperature and protect it from humidity. A loss of rheological and filtrate properties may result from inadequate storage.

Dosage & Mixing Instructions

We recommend mixing BRSBENT® SQ at a typical dosage range between 40–60 kg/m³ of water. BRSBENT® SQ shall be mixed for at least 30 minutes with a high shear mixer and develops its optimum rheology within 4 hours hydration time. For more information, please contact your representative.

1. Check the water quality (pH and EC) and pretreat with pH CONTROL® if needed.
2. Add the calculated amount of selected BRSBENT® SQ slowly into the mixer.
3. Mix the slurry intensely for at least 30 minutes.
4. Hydrate the slurry in the activation tanks with circulation for 4 hours to achieve optimum rheology.

Product Specification

Testing Method	CE Testing Method	
Tested at	50 g/l	
Mixer Type	GS-3S	
Rotation Speed	1100 rpm	
Mixing Time	5 minutes	
Water	Tap water	
Swelling Time	4 hours	
Fluid Property	Unit	Value
Marsh Viscosity	sec	≥ 100
Filtrate, 30 Minutes	ml	≤ 15
Decantation After 24 Hours	%	≤ 0.5
Six-speed Rotational Viscometer	mPa·s	≥ 80

Physical Properties

Property	Typical Value
Colour	Depends on the raw clay
Specific Weight	Approx. 2.6 g/cm ³
Bulk Density	900 – 1,100 kg/m ³
Swelling Volume, ASTM D5890	≥ 25 ml / 2 g
WSA (75 µm), API 13B-1	≤ 1 %
Moisture, API 13B-1	≤ 13 %

The technical information and application advice given in this Brighter Star Drilling Fluids publication are based on the present state of our best scientific and practical knowledge. As the information herein is of a general nature, no assumption can be made as to a product's suitability for a use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by law. The user is responsible for checking the suitability of products for their intended use.