

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: Gesso gamma 41[Chem]

SOP Name: GESSI.vsop

Edited: False

User Name: Antonio roberto

Edited On: 17 June 2014 17:33:45

Date: 17 June 2014 17:33:45

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 50x

Particles Counted: 10056

Result

CE Diameter Minimum (μm): 0.22

CE Diameter D[n, 0.1] (μm): 0.22

CE Diameter Maximum (μm): 55.12

CE Diameter D[n, 0.5] (μm): 3.45


CE Diameter Mean (μm): 4.26

CE Diameter D[n, 0.9] (μm): 10.17

CE Diameter STDV (μm): 4.83

CE Diameter RSD (%): 113.41

CE Diameter (μm) smoothed over 11 points



Record 111: Gesso gamma 41[Chem]

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com