

Technical Data Sheet

Calumex® Quick is a factory controlled pre-blend of basic Calumex® C.S.A. cement and 25% by weight of synthetic Anhydrite.

When mixed with Portland Cement to a ratio of 1 part Calumex® Quick to two parts of ordinary Portland cement, it will give the end product the following enhanced qualities;

- Rapid Set
- Early High Strength
- Increased strength in time
- Shrinkage compensation

Possible applications include; rapid repair mortars, fast setting tile adhesives and grouts, shotcrete, self-smoothing and self levelling mortars, anchor bolt and non shrink grouts and in all other applications where a rapid set and high early strength are required.

CALUMEX QUICK

CALCIUM SULPHO ALUMINATE CEMENT

Chemical Analysis

SiO ₂	≤	6 %
Al ₂ O ₃	≥	30 %
Fe ₂ O ₃	≤	1.4%
CaO	≥	25 %
MgO	≤	1.5%
SO ₃	≥	15 %
TiO ₂	≤	2.5%
LOI	≤	1.0%
Free Lime	≤	0.5%

Blaine	:	~ 4400 cm ² /g
Bulk density	:	~ 2,91 g/cm ³

CALTRA
NEDERLAND BV

Communicatieweg 21
Postbus 306
3640 AH Mijdrecht
NETHERLANDS

Tel: +31 297 289340
Fax: +31 297 289350
E-mail: support@caltra.com
Web: www.caltra.com

The information given above is based on our current experiences and knowledge of the product. It gives no guarantee of the eventual result. The customer remains responsible for testing the product before use. Caltra Nederland BV can not be held responsible for possible damage caused by (incorrect) use of it's products.