

Product Information

BERMOCOLL[®] M 30

BERMOCOLL[®] M 30 is a non-ionic, water soluble cellulose ether intended as a water retaining and consistency improving additive to cement based mortars. BERMOCOLL[®] M 30 contains methyl, ethyl and hydroxyethyl substituents giving a unique balance between workability and strength.

Specifications

BERMOCOLL[®] M 30 is a high viscosity grade of methyl ethyl hydroxyethyl cellulose.

Physical data

Appearance	whitish powder
Particle size	98 % < 600 µm
Water content	max 5 %
Salt content	max 6 %

Characteristics of aqueous solutions

pH (1 % solution)	neutral
Surface activity	weak
Viscosity at 20°C (Brookfield LV)	
1 % solution	2,500 – 3,500 mPa's

Applications

BERMOCOLL[®] M 30 is used in cement-based tile fix and joint mortars for improvement of workability, consistency, water retention and adhesion. Normal dosage in mortar is 0.3 - 0.7 % calculated on the dry mortar weight.

BERMOCOLL[®] M 30 is intended for dry mixing with other powder materials and should not be used for direct dissolving in water.

Packaging and Storage

BERMOCOLL[®] M 30 is packed in multiply paper bags with an inner polyethylene bag. Net weight 15 kg. We recommend emptying the bags from the bottom. The empty bags can be recycled or burned. In unopened bags, BERMOCOLL[®] M 30 can be stored for several years. In opened bags, the moisture content of BERMOCOLL[®] M 30 will be influenced by the air humidity.

At the temperatures above 250°C (480°F), charring of BERMOCOLL[®] M 30 will occur. At high temperatures and in contact with an open flame, BERMOCOLL[®] M 30 will burn slowly with the characteristics of cellulose.

CCD2510

9.9.2014



No representation or warranty, expressed or implied, is made as to the accuracy or completeness of the information or data contained herein and Akzo Nobel Chemicals AG shall have no obligation or liability whatsoever with respect to any such information or data, including, but not limited to, any liability for infringement of patent or other industrial property rights. Akzo Nobel Chemicals AG disclaims all implied warranties of merchantability and fitness for a particular purpose. Akzo Nobel Chemicals AG shall in no event be liable for incidental or consequential damages, including, without limitation, lost profit, loss of income, loss of business opportunity and any other related costs and expenses.