

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: FX 2300

SOP Name: MATERIE PRIME.vsop

Edited: False

User Name: Morphologi

Edited On: 10 April 2014 11:44:50

Date: 10 April 2014 11:44:50

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 20x

Particles Counted: 4932

Result

CE Diameter Minimum (μm): 0.54

CE Diameter D[n, 0.1] (μm): 1.22

CE Diameter Maximum (μm): 132.72

CE Diameter D[n, 0.5] (μm): 3.43


CE Diameter Mean (μm): 5.92

CE Diameter D[n, 0.9] (μm): 11.07

CE Diameter STDV (μm): 9.24

CE Diameter RSD (%): 155.95

CE Diameter (μm) smoothed over 11 points



Record 567: FX 2300

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com