

Product information

Dynasylan® 40

Ethyl polysilicate

Technical data

Properties and test methods	Value	Unit	Method
Flash point	> 62	°C	DIN 51755
Density (20 °C)	1.050 - 1.070	g/cm ³	DIN 51757
Viscosity (20 °C)	арргох. 5.0	mPa's	DIN 53015
SiO ₂ content	40.0 - 42.0	% by weight	AN-SAA 0851

Registrations

Dynasylan® 40

EINECS/ELINCS (EU):	Yes	
AICS (Australia):	Yes	
DSL/NDSL (Canada):	Yes	
PICCS (Philippines):	Yes	
TSCA (USA):	Yes	
IECS (P.R. China):	Yes	
ENCS (Japan):	Yes	
ECL (South Korea):	Yes	
REACH (Europe)	Registered	

Dynasylan® 40 is a ethyl silicate with a silicon dioxide content of approximately 40 - 42 % upon complete hydrolysis (the Si content of Dynasylan® 40 is calculated as SiO_2).

Dynasylan* 40 is formed in the presence of water from tetraethyl silicate (Si[OEt]4) by partial hydrolysis of the ethoxy groups to hydroxyl groups and subsequent condensation with formation of siloxane bonds (-Si-O-Si-).

Dynasylan® 40 is a colorless, low-viscosity liquid with an SiO₂ content of 40% (the Si content of Dynasylan® 40 is calculated as SiO₂). The polysilicic acids still have a sufficient content of ethoxy groups which can be activated by acid- or base-catalyzed hydrolysis. Condensation starts even during hydrolysis, with the formation of relatively large polymeric molecules. During storage of these hydrolysates, condensation continues until a gel is formed, where the rate depends on the degree of hydrolysis.

The action of the hydrolysates as binders is based on the continuation of the hydrolysis with subsequent gelation and dehydration to give polymeric SiO₂ structures.

Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website www.dynasylan.com or upon request from your local representative, customer service or from Evonik Resource Efficiency GmbH, Product Safety Department, E-MAIL sds-hu@evonik.com.

Packaging, storage and shelf life

Dynasylan® 40 is supplied ready to use in 25 kg, 220 kg drums or in 1.000 kg IBC containers.

In an unopened container Dynasylan® 40 has a shelf life of min. 12 months from delivery.

Properties and applications

Similarly to Dynasylan® A, Dynasylan® 40 is used to deposit silicic acid formed as a result of complete hydrolysis. The resulting silicic acid bonds well to many inorganic substrates, such as glass, ceramic, metal, fillers, pigments and synthetic fibers. The deposition of a thin SiO2 layer improves the chemical and thermal stability and mechanical properties.

Other applications are:

- crosslinker component in cold-curing silicone rubber systems
- binder, especially as a Dynasylan* 40 hydrolysates for molds used e.g. in the precision foundry industry.
- hardening component in dentistry for impression materials and as binder for embedding material

Dynasylan® 40 is also used as starting material for sol-gel processes. It is usually used in conjunction with alkylsilanes (e.g. Dynasylan® PTEO) organofunctional silanes and/or organic precursors(e.g. organic resins) to form siloxane networks. This makes it possible to obtain highly scratch-, abrasion- and chemical-resistant coatings.

Dynasylan® 40 is immiscible with water, so hydrolysis therefore requires a cosolvent as solubilizer. Mineral acids and ammonia are suitable as catalysts.

Dynasylan® 40 or its hydrolysates are also the binder component for 1- and 2-pack zinc dust paints, crucial for corrosion protection on steel.

Dynasylan® 40 as binder for 1-pack zinc dust paints

The hydrolysis and condensation reaction of Dynasylan® 40 is catalysed through via basic compounds such as diethanolamin. Dynasylan® 40 zinc dust paints or binders catalysed in such manner have an excellent storage stability (under exclusion of moisture). Through addition of a physically drying binder, such as an acrylate, the initial hardness of the coating can be improved dramatically.

Such zinc dust paints cure rapidly with ambient humidity through hydrolysis and condensation. Further information can be found in the product information of Dynasylan® MKS and S 100.

Dynasylan® 40 as binder in 2-pack zinc dust paints.

The binders are hydrolysates made by mixing of Dynasylan* 40 with selected solvents (e.g. alcohols, ethers), water, and an acid.

Important for the reaction behavior and storage stability is the amount of water added to the system. 2-pack systems usually have a SiO₂-content of about 20 % and a degree of hydrolysis of about 85 - 95%. The higher the amount of water that has been added, the lower the storage stability of the hydrolysate system.

The pH of the system is changed through the addition of zinc dust, and condensation starts. The pot life of such a hydrolysate will be about 8-16 hours.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

Europe/Middle-East/Africa/RoW Evonik Resource Efficiency GmbH

Business Line Silanes Rodenbacher Chaussee 4 63457 Hanau-Wolfgang Germany PHONE +49 6181 59 13636 FAX +49 6181 59 713915 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik (SEA) Pte. Ltd.

Business Line Silanes
3 Internatioanl Business Park
#07-18, Nordic European Centre
Singapore 609927
PHONE +65 6809 6576
FAX +65 6809 6699
dynasylan@evonik.com
www.dynasylan.com

Asia / Pacific Evonik Japan Co. Ltd

Business Line Silanes
12th Floor Monolith Building
2-3-1, Nishi-Shinjuku-ku
Tokyo 163-0912
Japan
PHONE +81 353 23 7446
FAX +81 353 23 7397
dynasylan@evonik.com
www.dynasylan.com

North America Evonik Corporation

Business Line Silanes
299 Jefferson Road
Parsippany, NJ 07054-0677
USA
PHONE (TOLL FREE) +1 800 237 67 45
PHONE +1 973 929 8513
FAX +1 973 929 8503
dynasylan@evonik.com
www.dynasylan.com

Asia / Pacific Evonik Specialty Chemicals (Shanghai) Co. Ltd.

Business Line Silanes
55, Chungdong Road
Xinzhuang Industry Park
Shanghai 201108
P.R. China
PHONE +86 21 61191-399
FAX +86 21 61191-648
dynasylan@evonik.com
www.dynasylan.com

Asia / Pacific Evonik India Pvt. Ltd.

Business Line Silanes
Krislon House
Saki Vihar Road, Anderi (E)
Mumbai - 400 072
India
PHONE +91 226 7238 809
FAX +91 226 7238 811
dynasylan@evonik.com
www.dynasylan.com

North America Silbond Corporation

9901 Sand Creek Highway Weston, MI 49289 USA PHONE +1 517 436 9316 FAX +1 517 436 3148 dynasylan@evonik.com www.dynasylan.com

Asia / Pacific Evonik Korea Ltd.

Business Line Silanes 94, Galsan 1-dong Bupyeong-gu Incheon, 403-081 Korea PHONE +82 2320 4773 FAX +82 2783 2520 dynasylan@evonik.com www.dynasylan.com

Latin America Evonik Brasil Ltda.

Business Line Silanes
Alameda Campinas, 579
01404-000 São Paulo-SP
Brazil
PHONE +55 11 3146 4123
FAX +55 11 3146 4148
dynasylan@evonik.com
www.dynasylan.com

Asia / Pacific Evonik Taiwan Ltd.

Business Line Silanes
Artist Construction Bldg.
9F, No. 133
Min Sheng East Road, Sec 3
Taipei, 105 Taiwan, R.O.C.
Taiwan 10596
PHONE +886 227 17 1242
FAX +886 227 17 2106
dynasylan@evonik.com
www.dynasylan.com

