

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: Aggregato da riciclo basalto

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 26 September 2014 15:00:21

Date: 04 September 2014 15:22:25

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 2.5x

Particles Counted: 521729

Result

CE Diameter Minimum (μm): 4.29

CE Diameter D[n, 0.1] (μm): 4.91

CE Diameter Maximum (μm): 1355.26

CE Diameter D[n, 0.5] (μm): 8.39


CE Diameter Mean (μm): 11.03

CE Diameter D[n, 0.9] (μm): 18.29

CE Diameter STDV (μm): 11.21

CE Diameter RSD (%): 101.65

CE Diameter (μm) smoothed over 11 points



Record 51: Aggregato da riciclo basalto

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com