## **HS Circularity - Number Distribution**



## Measurement Details

Sample Name: Mefisto L05[Chem]

SOP Name: MATERIE PRIME.vsop

User Name: roberto antonio

Date: 23 June 2014 18:11:18

Edited: False

Edited On: 23 June 2014 18:11:18

## Analysis

SOP Analysis: 3.0

SOP Segmentation: None

SOP Optic(s) used: 50x

SOP Fill Holes: True

SOP Trash Size: 10

## Result

**HS Circularity Minimum: 0.272** 

**HS Circularity Maximum: 0.769** 

HS Circularity Mean: 0.491

**Particles Counted: 715** 


HS Circularity D[n, 0.1]: 0.324

HS Circularity D[n, 0.5]: 0.475

HS Circularity D[n, 0.9]: 0.685

HS Circularity STDV: 0.134

HS Circularity RSD (%): 27.341



Comments:

Morphologi Malvern Instruments Worldwide www.malvern.com