## **HS Circularity - Number Distribution**



## Measurement Details

Sample Name: PENTACHEM PENTAMIX OS 10

Edited: True SOP Name: MATERIE PRIME.vsop

Edited On: 19 May 2014 17:48:34 **User Name:** 

Date: 19 May 2014 17:45:36

## Analysis

SOP Analysis: 3.0 SOP Fill Holes: True

SOP Trash Size: 10 SOP Segmentation: None

SOP Optic(s) used: 50x

## Result


**HS Circularity Minimum: 0.073** HS Circularity D[n, 0.1]: 0.238

**HS Circularity Maximum: 0.975** HS Circularity D[n, 0.5]: 0.464

HS Circularity Mean: 0.487 HS Circularity D[n, 0.9]: 0.768

Particles Counted: 2237 HS Circularity STDV: 0.194

HS Circularity RSD (%): 39.890



Comments:

Morphologi Malvern Instruments Worldwide www.malvern.com