

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: VINNAPAS 7220 E

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 08 May 2014 12:04:55

Date: 07 May 2014 18:59:11

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 10x

Particles Counted: 13565

Result

CE Diameter Minimum (μm): 1.08

CE Diameter D[n, 0.1] (μm): 1.35

CE Diameter Maximum (μm): 69.88

CE Diameter D[n, 0.5] (μm): 2.97


CE Diameter Mean (μm): 4.10

CE Diameter D[n, 0.9] (μm): 7.49

CE Diameter STDV (μm): 4.12

CE Diameter RSD (%): 100.54

CE Diameter (μm) smoothed over 11 points



Record 133: VINNAPAS 7220 E

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com