



Starting point formulation

CONSOLIDATING PRIMER. based on Carboset CA7147

Formulation number : 28.04.11
Origin : Sant Cugat, MIRP
Date : APR 11

Ingredients	Weight in gram	Description	Supplier
Carboset CA7147	20.00	Polymer	Lubrizol
Water	78.50		
Mergal 759	0.12	Biocide	Troy Chemical
Rheolate 350	0.50	Thickner	Elementis
BYK 023	0.50	Defoamer	BYK
BYK 345	0.38	Wetting agent	BYK
		<hr/>	
Total	100.00		

Viscosity Cup Ford No 4 10-15 seg
Density (gr/cc) 1.0+/-0.02

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance.

Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials Sales Spain, S.L. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials Sales Spain, S.L.'s direct control.

The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.
© 2007 The Lubrizol Corporation