


Customer	Portogallo
Sample ID	APB 300
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

CHEMICAL COMPOSITION: Quartz Sand

MOISTURE CONCENTRATION: 0%

#### Particles size distribution



#### Particles size analysis

Diameter (μm)	Passing (%)
600,00	99,99
500,00	99,98
300,00	94,40
212,00	45,78
125,00	10,94
80,00	2,65
63,00	0,49

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).