

	We offer first class, very high quality tested Bronzepulver		
	Composition 10.3% tin / 0.35% phosphorus / residual copper		
	Screen size analysis:> 45µm 0.1% <45µm 99.9%		
	Particle shape: spherical (spherical)		
	Form of manufacture: Air distortion		
	Fill density: 4.66 g / cm3		
	The powder is suitable for grinding, polishing, etc. as it does not have any luster effects in its basic form, After working with abrasive paper, sanding paste, etc., come to light You can mix this powder into any kind of binder or putty Please mix this powder very slowly but thoroughly Recommendation is applied to an already colored background so that the effects are more effective You can also mix several powders as long as they have no flaky structure		
	Signal word: Attention		
	H400 Very suitable for aquatic organisms		
	H412 Harmful to aquatic life with long lasting effects		
	No risk of explosion		
	Not self-igniting		
	Not dust-explosion-proof		
	Reactions with acids, alkalis, oxidizing agents		
	UN number: 3077		
This text can be edited at Content Manager -> Footer in the backend.			
-		Ti	
		This text can be edited at Content Manager -> Footer 3rd Column in the backend.	

This text can be edited at Content Manager -> Footer 4th Column in the backend.