

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: WALOCEL MKX 60000 CIMENTAL

SOP Name: MATERIE PRIME.vsop

Edited: False

User Name:

Edited On: 20 May 2014 17:20:49

Date: 20 May 2014 17:20:49

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 2.5x

Particles Counted: 32802

Result

CE Diameter Minimum (μm): 4.29

CE Diameter D[n, 0.1] (μm): 4.61

CE Diameter Maximum (μm): 272.99

CE Diameter D[n, 0.5] (μm): 9.39


CE Diameter Mean (μm): 21.17

CE Diameter D[n, 0.9] (μm): 56.26

CE Diameter STDV (μm): 26.14

CE Diameter RSD (%): 123.49

CE Diameter (μm) smoothed over 11 points



Record 100: WALOCEL MKX 60000 CIMENTAL

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com