


Customer	Portugal
Sample ID	Sand Areia Fina Amarela
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

CHEMICAL COMPOSITION: Silica Sand

MOISTURE CONCENTRATION: 15.66%

Particles size distribution



Particles size analysis

Diameter (µm)	Passante (%)
850	91,71
710	89,16
600	84,83
500	79,34
300	56,32
212	37,41
125	6,90
80	3,11
63	1,95

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).