

# Aspect Ratio - Number Distribution



## Measurement Details

**Sample Name:** SLAG CEMENT

**SOP Name:** CEMENTO CALME 42.5 R TIPO II.vsop

**Edited:** False

**User Name:** Morphologi

**Edited On:** 17 January 2014 14:17:24

**Date:** 17 January 2014 14:17:24

## Analysis

**SOP Analysis:** 3.0

**SOP Trash Size:** 10

**SOP Segmentation:** None

**SOP Fill Holes:** True

**SOP Optic(s) used:** 50x

## Result

**Aspect Ratio Minimum:** 0.156

**Aspect Ratio D[n, 0.1]:** 0.501

**Aspect Ratio Maximum:** 1.000

**Aspect Ratio D[n, 0.5]:** 0.728


**Aspect Ratio Mean:** 0.714

**Aspect Ratio D[n, 0.9]:** 0.900

**Particles Counted:** 15761

**Aspect Ratio STDV:** 0.151

**Aspect Ratio RSD (%):** 21.09



## Comments: