


Customer	Benin
Sample ID	Sable Fin - comp767
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

CHEMICAL COMPOSITION: Quartz Sand

MOISTURE CONCENTRATION: 0.4%

Particles size distribution



Particles size analysis

Diameter Sieve	Passing %
[μm]	-
710,00	94,86
600,00	92,73
500,00	89,58
300,00	65,02
250,00	43,94
125,00	1,58
80,00	0,16
63,00	0,09
f	0,00

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).