

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: Elotex FX3300

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name: Russo

Edited On: 05 March 2014 11:18:52

Date: 05 March 2014 11:08:40

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 50x

Particles Counted: 1004

Result

CE Diameter Minimum (μm): 0.22

CE Diameter D[n, 0.1] (μm): 0.30

CE Diameter Maximum (μm): 30.27

CE Diameter D[n, 0.5] (μm): 2.07


CE Diameter Mean (μm): 3.65

CE Diameter D[n, 0.9] (μm): 8.69

CE Diameter STDV (μm): 4.49

CE Diameter RSD (%): 123.05

CE Diameter (μm) smoothed over 11 points



Record 85: Elotex FX3300

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com