## CE Diameter Report - Number Distribution



Measurement Details

Sample Name: Carbonato di Calcio Femia

**SOP Name:** Calci.vsop **Edited:** False

User Name: Domenco Edited On: 19 December 2014 17:56:38

Date: 19 December 2014 17:56:38

Analysis

SOP Analysis: 3.0 SOP Fill Holes: True

**SOP Segmentation**: None **SOP Trash Size**: 10

SOP Optic(s) used: 50x Particles Counted: 245935


Result

CE Diameter Minimum (µm): 0.22 CE Diameter D[n, 0.1] (µm): 0.57

CE Diameter Maximum (µm): 76.58 CE Diameter D[n, 0.5] (µm): 3.51

CE Diameter Mean (µm): 4.35 CE Diameter D[n, 0.9] (µm): 8.58

CE Diameter STDV (µm): 3.76 CE Diameter RSD (%): 86.50



Comments:

Morphologi Malvern Instruments Worldwide www.malvern.com