

Elongation - Number Distribution



Measurement Details

Sample Name: SLAG CEMENT

SOP Name: CEMENTO CALME 42.5 R TIPO II.v SOP

User Name: Morphologi

Date: 17 January 2014 14:17:24

Edited: False

Edited On: 17 January 2014 14:17:24

Analysis

SOP Analysis: 3.0

SOP Segmentation: None

SOP Optic(s) used: 50x

SOP Fill Holes: True

SOP Trash Size: 10

Result

Elongation Minimum: 0.000

Elongation Maximum: 0.844

Elongation Mean: 0.286

Particles Counted: 15761

Elongation D[n, 0.1]: 0.097


Elongation D[n, 0.5]: 0.269

Elongation D[n, 0.9]: 0.497

Elongation STDV: 0.151

Elongation RSD (%): 52.61

Elongation smoothed over 11 points



Record 55: SLAG CEMENT

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com