

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: VINNAPAS 8031 H (WACKER)

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 28 May 2014 11:39:02

Date: 28 May 2014 10:33:41

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 20x

Particles Counted: 8630

Result

CE Diameter Minimum (μm): 0.54

CE Diameter D[n, 0.1] (μm): 0.99

CE Diameter Maximum (μm): 90.34

CE Diameter D[n, 0.5] (μm): 3.36


CE Diameter Mean (μm): 5.75

CE Diameter D[n, 0.9] (μm): 12.25

CE Diameter STDV (μm): 7.43

CE Diameter RSD (%): 129.26

CE Diameter (μm) smoothed over 11 points



Record 162: VINNAPAS 8031 H (WACKER)

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com