VENATOR

Venator Italy S.r.I.

Località Casone - 58020 Scarlino(GR)-ITALY - Tel. 056671111 - Fax 056671130
Cap.Soc. 64.030.932 - C.F. 06186660152 - P.IVA 01149920538
S.r.I a Socio Unico - Reg. Imprese di Grosseto 1997/117394 - C.I.A.A. di Grosseto Societa del Gruppo Venator Materials International UK Limited

Shipment Test Results

| Seller's Ref Printed

20/03/2019

513841 / 80925445

Customer Reschem Deposito C/O Docks Srl Via Dei Boschi, 39

Isotta Ventura 20014 Nerviano Italy

Customer number

45273

Despatch Date 19/03/2019	Vehicle Number FL044MV XA354FZ	Vessel	Container Number	Supplying Factory/Warehouse SCARLINO	
Buyer's Reference S-ORA-00502 / 08/03/2019		Tioxide Contact	Product RXL_AA		

		BATCH NUMBER		
PROPERTY/TEST METHOD	UOM	1903004		
Al2O3 [SAMM 5.2.01]	%	4,80		
As [SAMM 4.1.01.16]	ppm	1,0		
Carbon [SAMM 4.1.01.30]	%	0,03		
Colour ^B [SPTM 1310]		0,02		
Colour ^L [SPTM 1310]		0,10		
Conductivity [SAMM 4.1.01.28]	μS/cm	127,8		
Dry Colour ^B [SPTM 102]		-0,01		
Dry Colour ^L [SPTM 102]		0,11		
Fe [SAMM 5.2.23]	ppm	48,3		
Loss @ 105°C [SPTM 1811]		1,60		
Opacity ^Y [SPTM 1310]		0,37		
PO4 (as P2O5) [SAMM 5.2.13]	%	0,08		
pH [SAMM 4.1.01.29]		8,1		
Sieve Residue [SPTM 1113]	ppm	50,00		
Rutile [PMM 204]	%	99,77		
Sb2O3 [SAMM 5.2.02]	ppm	7,00		
SiO2 [SAMM 5.2.15]	%	9,34		
TiO2 [SAMM 4.1.01.01]	%	80,20		
Tint Reduction [SPTM 1310]		0,31		
Pb+Cd+Cr+Hg [SAMM 4.1.01.70]	ppm	6,3		
Undertone [SPTM 1310]		0,07		
Water Demand [SPTM 150]	ml/min	58,00		
ZnO [SAMM 5.2.19]	ppm	0,01		
ZrO2 [SAMM 5.2.12]	%	0,03		

	1		
		Signature	Date
			20/03/2019

SUBJECT TO VENATOR STANDARD TERMS AND CONDITIONS OF SALE 201706S