

Product information

NAMEX® XA

**Expansive additive
for reduced thermal shrinkage of cement based products.**

Description

NAMEX® XA is a highly efficient addition, made up from a special mineral mix and milled to the particle size of cement. NAMEX® XA has been modified to reduce and compensate the thermal shrinkage of cement based construction products.

NAMEX® XA reacts with water with expanding volume.

Chemical composition (M.-%, ca.)

MgO	> 80 %	CaO	5 %
SiO ₂	4 %	Fe ₂ O ₃	2 %
Cl	< 0.1 %		

Physical properties

Appearance	off-white, easy handling and flowing powder		
Specific density	3,6 g/cm ³		
Apparent density	loose	0,6 g/cm ³	
	tapped	0,7 g/cm ³	
particle size	> 200 µ	< 1 %	
	< 90 µ	> 80 %	

Function

The mineral parts of NAMEX® XA react with water producing new hydration products. Together with the hardening phase of the cement these will produce a volume increase (expansion). This structure contains a pre-stress that will counteract the tensioning stresses of concrete in its cooling phase.

Advantages

Depending on the addition level:

- reduced shrinkage
- increased impermeability to water
- increased mechanical strength

and ease of handling.

Applications

NAMEX® XA can be used in a variety of applications, such as:

- high density mortars and concrete
- industrial flooring
- tile adhesives
- flooring

To give the required expansion, it is necessary to assure enough availability of water and use curing compounds.

Addition level

Typical addition levels are 3 – 6 % on the cement weight. Expansion and reduced shrinkage are proportional to the addition level. It is highly recommended that laboratory trials should first be carried out to determine the correct addition level of NAMEX® XA.

A too high addition level of NAMEX® XA will result in extremely strong expansion, with reduced strength, high porosity and reduced frost resistance.

Compatibility

NAMEX® XA is compatible with Portland cement and hydraulic binders, including ground blast furnace slag, fly ash and hydrated lime.

Health & Safety

NAMEX® XA is alkaline and should be handled like other cements. Avoid contact with skin or eyes and wear protective gloves and goggles. In case of contact with eye flush immediately with plenty of water. Refer to Material Safety Data Sheet for full details.

Storage

NAMEX® XA is sensitive to moisture and should be stored in cool, dry conditions.

Packaging

Packed in 25 kg plastic bags, 40 bags per pallet

or packed in big bags of 1000kg (on request)

bulk is possible

The above information and recommendations are based upon our experience and are offered merely for advice. They do not absolve the consumer from making his own tests. Responsibility for damage arising from the use of our products cannot be derived from the recommendations given. The observance of any intellectual property rights of third parties is the responsibility of the consumer in each case.

MDS NAMEX® XA 2017-02 – v4e