

HS Circularity - Number Distribution



Measurement Details

Sample Name: FX 2322

SOP Name: MATERIE PRIME.vsop

User Name: Morphologi

Date: 09 April 2014 20:31:44

Edited: False

Edited On: 09 April 2014 20:31:44

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 20x

Result

HS Circularity Minimum: 0.057

HS Circularity D[n, 0.1]: 0.317

HS Circularity Maximum: 1.000

HS Circularity D[n, 0.5]: 0.537


HS Circularity Mean: 0.540

HS Circularity D[n, 0.9]: 0.751

Particles Counted: 4931

HS Circularity STDV: 0.164

HS Circularity RSD (%): 30.290



Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com