## **HS Circularity - Number Distribution**



## Measurement Details

Sample Name: Zeolite 5A

SOP Name: Materie prime 2.vsop

**User Name:** 

Date: 06 May 2014 20:14:05

Edited: False

Edited On: 06 May 2014 20:14:05

## Analysis

SOP Analysis: 3.0 SOP Fill Holes: True

SOP Segmentation: None SOP Trash Size: 10

SOP Optic(s) used: 50x

## Result


HS Circularity Minimum: 0.003 HS Circularity D[n, 0.1]: 0.480

HS Circularity Maximum: 0.995 HS Circularity D[n, 0.5]: 0.791

HS Circularity Mean: 0.744 HS Circularity D[n, 0.9]: 0.924

Particles Counted: 8093 HS Circularity STDV: 0.177

HS Circularity RSD (%): 23.836



Comments:

Morphologi Malvern Instruments Worldwide www.malvern.com