

CE Diameter Report - Number Distribution



Measurement Details

Sam... SODIO GLUCONATO - EIGENMANN & V...

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 20 May 2014 12:04:42

Date: 20 May 2014 12:00:09

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 5x

Particles Counted: 99614

Result

CE Diameter Minimum (μm): 2.16

CE Diameter D[n, 0.1] (μm): 2.77

CE Diameter Maximum (μm): 657.55

CE Diameter D[n, 0.5] (μm): 5.79


CE Diameter Mean (μm): 8.08

CE Diameter D[n, 0.9] (μm): 14.76

CE Diameter STDV (μm): 9.60

CE Diameter RSD (%): 118.83

CE Diameter (μm) smoothed over 11 points



Record 96: SODIO GLUCONATO - EIGENMANN & VERONELLI

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com