

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: PENTACHEM - PENTARAPID 99

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 14 May 2014 12:34:39

Date: 14 May 2014 12:32:35

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 10x

Particles Counted: 32191

Result

CE Diameter Minimum (μm): 1.08

CE Diameter D[n, 0.1] (μm): 1.48

CE Diameter Maximum (μm): 141.78

CE Diameter D[n, 0.5] (μm): 3.54


CE Diameter Mean (μm): 5.09

CE Diameter D[n, 0.9] (μm): 8.56

CE Diameter STDV (μm): 6.78

CE Diameter RSD (%): 133.17

CE Diameter (μm) smoothed over 11 points



Record 48: PENTACHEM - PENTARAPID 99

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com