

CE Diameter Report - Number Distribution



Measurement Details

Sample Na... CEMENTO BIANCO 42.5 R ROCCABIAN...

SOP Name: MATERIE PRIME.vsop

Edited: False

User Name:

Edited On: 21 July 2014 19:41:16

Date: 21 July 2014 19:41:16

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 50x

Particles Counted: 13322

Result

CE Diameter Minimum (μm): 0.22

CE Diameter D[n, 0.1] (μm): 0.25

CE Diameter Maximum (μm): 50.32

CE Diameter D[n, 0.5] (μm): 2.43


CE Diameter Mean (μm): 3.36

CE Diameter D[n, 0.9] (μm): 7.46

CE Diameter STDV (μm): 3.63

CE Diameter RSD (%): 108.08

CE Diameter (μm) smoothed over 11 points



Record 19: CEMENTO BIANCO 42.5 R ROCCABIANCA

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com