

Product Data Sheet: Polymer HD7560

Polymer HD7560 is a waterborne, free from NMP as well as NEP, hydrophobic, bio based, aliphatic polyurethane dispersion.

Typical properties:

Type:	Aliphatic polyurethane dispersion
Appearance:	Yellowish/Bluish, slightly hazy liquid
Solids content (%):	36 ± 1 %
pH:	7.0 – 8.0
Viscosity (25°C; mPa·s):	10 – 70
Mean particle size (nm):	30 – 70
MFFT (°C):	0
Hardness (König Sec.)	140
Solvent content:	5 % DMM
Neutralization:	Amine
Preservatives:	MIT <100ppm ; BIT <100ppm

Film Properties:

- Excellent chemical and scuff resistance
- Excellent Water resistance
- Good Flow-Out
- Good Film Clarity
- Good toughness / hardness balance
- High abrasion resistance
- Good scratch resistance

Recommendation for end-use:

- Wood – Joinery & Floor
- Plastics
- Metals

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent. All sales of these products shall be subject to BW Resins standard conditions of sales.

Guide Formulation 1

Water based glossy parquet finish Based on Polymer HD7560

No.	Ingredient	Parts by Weight	Type of material
1	Polymer HD7560	85.0	Binder
2	Demi Water	4.2	n.a.
3	Dowanol DPM	3.0	Coalescent
4	Dowanol DPnB	1.3	Coalescent
5	Demi Water	1.3	n.a.
6	Byk 347	0.1	Levelling agent
7	Aquacer 515	4.3	Wax
8	Acrysol RM-825	0.2	Thickener
9	Byk 093	0.6	Defoamer

		100.0	

Preparation:

Add 1 to 8 in order listed at moderate speed.

Pre-mix ingredients 3 to 5.

Disperse ingredient 9 until crater free.

Specifications:

Solids (%w/w)	32.9
VOC (%)	5.1