


Customer	Portugal
Sample ID	Sand Areia Fina Braca
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

CHEMICAL COMPOSITION: Silica Sand

MOISTURE CONCENTRATION: 11,11%

Particles size distribution



Particles size analysis

Diameter (μm)	Passing (%)
850	96,99
710	94,94
600	91,59
500	86,18
300	62,35
212	38,39
125	8,31
80	3,04
63	1,32

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).