

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: Filler DIMANNO

SOP Name: MATERIE PRIME.vsop

Edited: False

User Name: Morphologi

Edited On: 28 April 2015 10:18:08

Date: 28 April 2015 10:18:08

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 50x

Particles Counted: 19072

Result

CE Diameter Minimum (μm): 0.22

CE Diameter D[n, 0.1] (μm): 1.18

CE Diameter Maximum (μm): 49.93

CE Diameter D[n, 0.5] (μm): 3.12


CE Diameter Mean (μm): 4.09

CE Diameter D[n, 0.9] (μm): 8.07

CE Diameter STDV (μm): 3.34

CE Diameter RSD (%): 81.83

CE Diameter (μm) smoothed over 11 points



Record 22: Filler DIMANNO

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com