## CE Diameter Report - Number Distribution



Measurement Details

Sample Name: VINNAPAS 5020 L (Wacker)

SOP Name: MATERIE PRIME.vsop Edited: True

**User Name:** Edited On: 22 May 2014 16:20:49

Date: 22 May 2014 16:17:11

Analysis

SOP Analysis: 3.0 SOP Fill Holes: True

**SOP Segmentation**: None **SOP Trash Size**: 10

SOP Optic(s) used: 20x Particles Counted: 23198


Result

CE Diameter Minimum (µm): 0.54 CE Diameter D[n, 0.1] (µm): 0.93

CE Diameter Maximum (µm): 118.77 CE Diameter D[n, 0.5] (µm): 2.61

CE Diameter Mean (µm): 4.74 CE Diameter D[n, 0.9] (µm): 10.14

CE Diameter STDV (µm): 6.38 CE Diameter RSD (%): 134.52



Comments:

Morphologi Malvern Instruments Worldwide www.malvern.com