


Customer	Dal Tile
Sample ID	QUARTZ SAND ROOF-OK. Comp637
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

#### CHEMICAL COMPOSITION:QUARTZ SAND

MOISTURE CONCENTRATION: 0 %

#### Particles size distribution



#### Particles size analysis

Diameter (μm)	Passing (%)
500	99,98
355	99,65
212	75,02
125	11,97
80	0,55
63	0,09

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).