# HS Circularity - Number Distribution

**Malvern**

## Measurement Details

**Sample Name:** VINNAPAS LL 5111  L (WACKER)

**SOP Name:** MATERIE PRIME.vsop

**User Name:**

**Date:** 26 May 2014 13:19:35

**Edited:** True

**Edited On:** 26 May 2014 14:24:35

## Analysis

**SOP Analysis:** 3.0

**SOP Segmentation:** None

**SOP Optic(s) used:** 20x

**SOP Fill Holes:** True

**SOP Trash Size:** 10

## Result

**HS Circularity Minimum:** 0.143

**HS Circularity Maximum:** 1.000

**HS Circularity Mean:** 0.814

**Particles Counted:** 2849

**HS Circularity D[n, 0.1]:** 0.537

**HS Circularity D[n, 0.5]:** 0.877

**HS Circularity D[n, 0.9]:** 0.968

**HS Circularity STDV:** 0.173

**HS Circularity RSD (%):** 21.284



HS Circularity smoothed over 11 points

Record 148: VINNAPAS LL 5111  L (WACKER)

**Comments:**

Morphologi

Malvern Instruments Worldwide

www.malvern.com