


Customer	Dal Tile
Sample ID	Quartz Sand Cleburne TX comp636
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

CHEMICAL COMPOSITION: QUARTZ SAND

MOISTURE CONCENTRATION: 0 %

Particles size distribution



Particles size analysis

Diameter (μm)	Passing (%)
500	99,56
355	95,52
212	42,96
125	5,15
80	0,66
63	0,23

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).