

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: VINNAPAS 5023 L (Wacker)

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 22 May 2014 12:31:28

Date: 22 May 2014 12:28:24

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 10x

Particles Counted: 34021

Result

CE Diameter Minimum (μm): 1.08

CE Diameter D[n, 0.1] (μm): 1.90

CE Diameter Maximum (μm): 125.32

CE Diameter D[n, 0.5] (μm): 5.35


CE Diameter Mean (μm): 6.82

CE Diameter D[n, 0.9] (μm): 12.21

CE Diameter STDV (μm): 6.25

CE Diameter RSD (%): 91.66

CE Diameter (μm) smoothed over 11 points



Record 119: VINNAPAS 5023 L (Wacker)

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com