Sheet2

Sabbia Fine II Arkein

Sieve	Passing
(µm)	(%)
710	100,00
600	100,00
500	99,97
355	92,49
300	81,62
250	59,07
212	43,33
180	23,96
100	3,75

