


Customer	
Sample ID	Silica Sand (70% Quarzo, 25% Silicea, 5% Calcare)
Test	AGGREGATES CHARACTERIZATION
Sample (g)	300
Lab address	PF Lab Services – Simbario (VV) – ITALY

#### CHEMICAL COMPOSITION: Silica Sand

MOISTURE CONCENTRATION: 0%

#### Particles size distribution



#### Particles size analysis

Diameter (μm)	Passing (%)
850	99,95
710	99,93
600	99,90
500	99,54
300	51,84
212	23,39
125	4,18
80	1,44
63	0,61

For the analysis were used Sieves mesh mall S Steel I.S.O. 3310 (UNI EN 933-2) and electric sieve shaker with timer (UNI EN 932-5 ISO 3310-1).