

CARBOSET® CA7147

Acrylic Polymer Emulsion

Applications	Exterior elastic paints for facades, both for pale and deep colors.	
Performance	<ul style="list-style-type: none">• Excellent water washability and scrubbability.• Fast hardening and water resistance.• Excellent binding power for fillers and pigments.• Fine particle size.• Easy application.• Excellent spreading and brushability.• Provides long-lasting brightness to colours.• Excellent weathering and yellowing resistance.• Excellent gloss.• Low thermoplasticity and low dirty pick up.• Alkyl Phenol Ethoxylate (APE) free.	
Typical properties	pH	8 – 9
	Alkali	Ammonia
	Total Solids %	46 - 48
	Viscosity Brookfield at 25°C (cps)	200 - 800
	Alkali	Ammonia
	MFFT (°C)	6
	Particle Size	70 - 120
	Emulsifier	Anionic Surfactants
Packaging and storage	The product should be stored in places safe from sunlight and excessive cold in original closed packages. It should be used within one year from manufacturing date.	

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variations in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the applications disclosed. Full-scale testing and end product performance are the responsibility of the user. Lubrizol Advanced Materials Sales Spain, S.L. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials Sales Spain, S.L.'s direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

