

VINNAPAS® 2012 E (VINNAPAS® 2012 N)

Product description

Product description

VINNAPAS® 2012 E (VINNAPAS® 2012 N) is especially well-suited for repair mortar, and giving the end product a high degree of strength and water resistance.

Properties

VINNAPAS® 2012 E (VINNAPAS® 2012 N) is an acrylic acid ester copolymer powder. It is dispersible in water and has excellent saponification resistance. Compounds modified with VINNAPAS® 2012 E (VINNAPAS® 2012 N) exhibit improved adhesion, flexural strength in bending, deformability, abrasion resistance and are easier to process. Leveling, thixotropy and water retention are essentially unaffected. The product is ideal for use in combination with other mortar additives intended to enhance specific properties.

VINNAPAS® 2012 E (VINNAPAS® 2012 N) contains a fine mineral filler as an antiblocking agent. It is free of solvents, plasticizers and film-forming agents.

Special features

VINNAPAS® 2012 E (VINNAPAS® 2012 N) has no effect on rheological properties and is a low-emissions, general-purpose powder in the medium Tg range. It is eminently suitable for formulating compounds of high ultimate strength.

Application

For typical application fields of VINNAPAS® 2012 E (VINNAPAS® 2012 N) you can refer to the following application table. Please discuss additional applications with your WACKER customer representative.

Application	Recommendation	Suitability
Concrete repair mortars	PCC	●
Tile adhesives EN 12004/12002 C1/C2	Thin-bed mortars	●
	Flow-bed mortars	●
Cementitious screeds	Indoor	●
	Outdoor	●
Floor/Wall troweling compounds	Fine leveling compounds	○
	Coarse leveling compounds	○
● highly recommended ○ recommended		

Processing

For the production of ready-mixed powders, such as dry mortars, adhesives and troweling compounds, blend VINNAPAS® 2012 E (VINNAPAS® 2012 N) with the other dry ingredients in appropriate equipment. Temperatures should not be allowed to rise excessively during mixing because otherwise the dispersible polymer powder could agglomerate and lead to the formation of small lumps of resin. The mortar or troweling compound is prepared for use by adding the recommended amount of water and mixing by hand or machine. Since hand mixing generates little shear force, we recommend allowing the fresh mortar to slake for 5 minutes and then stirring it again. This is usually unnecessary where mechanical mixers are employed.

Storage

VINNAPAS® 2012 E (VINNAPAS® 2012 N) should be stored in a cool place and protected against moisture. Since the product is thermoplastic, it should not be subjected to pressure or high temperatures during storage because of the risk of caking. Storage time should not exceed 6 months from receipt of delivery. Blends with hydraulic binders, fillers and pigments show better storage stability because these components help to prevent caking. However, blends of this type still have to be protected against moisture.

Packaging

25 kg paper bags.

Big Bags (sizes on request).
Bulk on request.

Slight discoloration may occur without impairing the product's functionality.

Additional information

If VINNAPAS® 2012 E (VINNAPAS® 2012 N) is used in applications other than those mentioned, the choice, processing and use of VINNAPAS® 2012 E (VINNAPAS® 2012 N) is the sole responsibility of the purchaser. All legal and other regulations must be complied with.

Safety notes

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

Product data

Specification data	Inspection Method	Value
Solids content	DIN EN ISO 3251	98 - 100 %
Ash Content	specific method	11 - 15 %
Bulk density	DIN EN ISO 60	350 - 550 kg/m ³

Typical general characteristics	Inspection Method	Value
Appearance	Visual	white powder
Protective colloid / emulsifier system	specific method	polyvinyl alcohol
Particle size	DIN EN ISO 4610	Max. 2 % over 400 µm
Predominant particle size redispersion	specific method	0,5 - 10 µm
Minimum film forming temperature	DIN ISO 2115	5 °C
Film properties of the redispersion	specific method	cloudy, tough-elastic

These figures are only intended as a guide and should not be used in preparing specifications.

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER is a trademark of Wacker Chemie AG.
VINNAPAS® is a trademark of Wacker Chemical Corporation.

For technical, quality, or product safety questions, please contact:

Wacker Chemical Corporation
3301 Sutton Road
Adrian, Michigan 49221-9397, USA
info.polymers@wacker.com

www.wacker.com