

CE Diameter Report - Number Distribution



Measurement Details

Sample Name: VINNAPAS LL 3030 H (WACKER)

SOP Name: MATERIE PRIME.vsop

Edited: True

User Name:

Edited On: 26 May 2014 10:32:11

Date: 26 May 2014 10:26:25

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 20x

Particles Counted: 7647

Result

CE Diameter Minimum (μm): 0.54

CE Diameter D[n, 0.1] (μm): 0.87

CE Diameter Maximum (μm): 92.53

CE Diameter D[n, 0.5] (μm): 3.14


CE Diameter Mean (μm): 4.76

CE Diameter D[n, 0.9] (μm): 9.27

CE Diameter STDV (μm): 6.14

CE Diameter RSD (%): 129.04

CE Diameter (μm) smoothed over 11 points



Record 140: VINNAPAS LL 3030 H (WACKER)

Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com