

# Dynasylan® 4148

## Polyethyleneglycol-functional alkoxysilane

### Technical data

Properties and test methods	Value	Unit	Method
Viscosity (20 °C)	10 - 20	mPa.s	DIN 53015
Freezing point	< - 10	°C	DIN ISO 3016
Density (20 °C)	approx. 1.1	g/cm <sup>3</sup>	DIN 51757
Flash point	> 95	°C	EN 22719

### Registrations

#### Dynasylan® 4148

AICS (Australia):	No
DSL/NDSL (Canada):	Yes
PICCS (Philippines):	No
TSCA (USA):	Yes
IECSC (P.R. China):	Yes
ENCS (Japan):	Yes
ECL (South Korea):	Yes
EINECS/ELINCS (EU):	Yes
REACH (Europe)	Exempted

Dynasylan® 4148 is a ready-for-use silane and is soluble in water and most organic solvents.

Dynasylan® 4148 helps to control rheological properties and to reduce viscosity in highly-filled polymer systems, like aluminum trihydroxide-filled polyesters or SMC-pastes.

Contrary to most other organofunctional silanes, Dynasylan® 4148 features chemical polarity yet remaining chemically not reactive. Such a product is used as a hydrophilic compatibilizer rather than a covalent adhesion promoter.

Dynasylan® 4148 permits workable viscosities at well over 250 phr aluminum trihydroxide loading in unsaturated polyester resins. Further more, Dynasylan® 4148 can be used as anti-settling agent for corrosion inhibitors in glycol based cooling agents.

As a non-coupling silane Dynasylan® 4148 can also be used as a slipping agent to simply modify a surface.

### Safety and handling

Before considering the use of Dynasylan® products please read its Safety Data sheet (SDS) thoroughly for safety and toxicological data as well as for information on proper transportation, storage and use. The Safety Data Sheet is available after registration on our website [www.dynasylan.com](http://www.dynasylan.com) or upon request from your local representative, customer service or from Evonik Operations GmbH, Product Safety Department, E-MAIL [sds-hu@evonik.com](mailto:sds-hu@evonik.com).

### Packaging, storage and shelf life

Dynasylan® 4148 is supplied in pails with a capacity of 25 kg and drums with 200 kg.

The containers must remain tightly sealed during storage and kept in a well aired place. Protection against humidity is essential.

Protect from frost (avoid temperatures below 0°C). The product becomes a solid when stored cold (e.g. at -10°C) but can be recovered without deterioration after melting.

In the unopened container Dynasylan® 4148 has a shelf life of min. 12 months from delivery.

## Properties and applications

Dynasylan® 4148 can be added neatly to a blend of filler or pigment and resin, or it can be used for the pretreatment of the filler or pigment.

Pre-treatment of the filler or pigment is best achieved in a high-speed mixer by spraying Dynasylan® 4148 into a well-agitated filler or pigment bed. In order to obtain maximum efficiency of the treated filler or pigment, a good distribution of Dynasylan® 4148 throughout the filler or pigment surface is essential.

If the surface area of a filler or pigment is unknown, 1 percent by weight of Dynasylan® 4148, based on filler or pigment, is a convenient initial basis for Pre-treatment. Subsequently, the exact Dynasylan® 4148 loading should be determined empirically.

Moreover, Dynasylan® 4148 can act as a lubricant and wetting agent in the glass fibre industry in combination with silane coupling agents.

As a non-coupling silane, Dynasylan® 4148 can dramatically reduce the dispersion viscosity of aluminum trihydroxide and many other fillers and pigments. Because of better wetting and dispersion, outstanding filler or pigment loadings at a given viscosity can be realized with Dynasylan® 4148.

Dynasylan® 4148 helps to increase pigment dispersion predominantly in aqueous media, thus leading to an enhanced gloss of a typical coating.

This information and any recommendations, technical or otherwise, are presented in good faith and believed to be correct as of the date prepared. Recipients of this information and recommendations must make their own determination as to its suitability for their purposes. In no event shall Evonik assume liability for damages or losses of any kind or nature that result from the use of or reliance upon this information and recommendations. EVONIK EXPRESSLY DISCLAIMS ANY REPRESENTATIONS AND WARRANTIES OF ANY KIND, WHETHER EXPRESS OR IMPLIED, AS TO THE ACCURACY, COMPLETENESS, NON-INFRINGEMENT, MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE) WITH RESPECT TO ANY INFORMATION AND RECOMMENDATIONS PROVIDED. Reference to any trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. Evonik reserves the right to make any changes to the information and/or recommendations at any time, without prior or subsequent notice.

**Europe/Middle-East/Africa/RoW  
Evonik Resource Efficiency GmbH**

Business Line Silanes  
Rodenbacher Chaussee 4  
63457 Hanau-Wolfgang  
Germany  
PHONE +49 6181 59 13636  
FAX +49 6181 59 713915  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific  
Evonik (SEA) Pte. Ltd.**

Business Line Silanes  
3 Internatioanl Business Park  
#07-18, Nordic European Centre  
Singapore 609927  
PHONE +65 6809 6576  
FAX +65 6809 6699  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific  
Evonik Japan Co. Ltd**

Business Line Silanes  
12th Floor Monolith Building  
2-3-1, Nishi-Shinjuku-ku  
Tokyo 163-0912  
Japan  
PHONE +81 353 23 7446  
FAX +81 353 23 7397  
dynasytan@evonik.com  
www.dynasytan.com

**North America  
Evonik Corporation**

Business Line Silanes  
299 Jefferson Road  
Parsippany, NJ 07054-0677  
USA  
PHONE (TOLL FREE) +1 800 237 67 45  
PHONE +1 973 929 8513  
FAX +1 973 929 8503  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific  
Evonik Specialty  
Chemicals (Shanghai) Co. Ltd.**

Business Line Silanes  
55, Chungdong Road  
Xinzhuang Industry Park  
Shanghai 201108  
P.R. China  
PHONE +86 21 61191-399  
FAX +86 21 61191-648  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific  
Evonik India Pvt. Ltd.**

Business Line Silanes  
Krislon House  
Saki Vihar Road, Anderi (E)  
Mumbai - 400 072  
India  
PHONE +91 226 7238 809  
FAX +91 226 7238 811  
dynasytan@evonik.com  
www.dynasytan.com

**North America  
Silbond Corporation**

9901 Sand Creek Highway  
Weston, MI 49289  
USA  
PHONE +1 517 436 9316  
FAX +1 517 436 3148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific  
Evonik Korea Ltd.**

Business Line Silanes  
94, Galsan 1-dong  
Bupyeong-gu  
Incheon, 403-081  
Korea  
PHONE +82 2320 4773  
FAX +82 2783 2520  
dynasytan@evonik.com  
www.dynasytan.com

**Latin America  
Evonik Brasil Ltda.**

Business Line Silanes  
Alameda Campinas, 579  
01404-000 São Paulo-SP  
Brazil  
PHONE +55 11 3146 4123  
FAX +55 11 3146 4148  
dynasytan@evonik.com  
www.dynasytan.com

**Asia / Pacific  
Evonik Taiwan Ltd.**

Business Line Silanes  
Artist Construction Bldg.  
9F, No. 133  
Min Sheng East Road, Sec 3  
Taipei, 105 Taiwan, R.O.C.  
Taiwan 10596  
PHONE +886 227 17 1242  
FAX +886 227 17 2106  
dynasytan@evonik.com  
www.dynasytan.com