

# CE Diameter Report - Volume Distribution



## Measurement Details

**Sample Name:** Vinnapas 7055E

**SOP Name:** MATERIE PRIME.vsop

**Edited:** True

**User Name:** Morphologi

**Edited On:** 14 April 2014 09:58:36

**Date:** 14 April 2014 09:40:58

## Analysis

**SOP Analysis:** 3.0

**SOP Fill Holes:** True

**SOP Segmentation:** None

**SOP Trash Size:** 10

**SOP Optic(s) used:** 20x

## Result

**CE Diameter Minimum ( $\mu\text{m}$ ):** 0.54

**CE Diameter D[v, 0.1]:** 31.55

**CE Diameter Maximum ( $\mu\text{m}$ ):** 148.19

**CE Diameter D[v, 0.5]:** 81.67

**CE Diameter D[4,3] ( $\mu\text{m}$ ):** 87.09

**CE Diameter D[v, 0.9]:** 147.1


**CE Diameter D[3,2] ( $\mu\text{m}$ ):** 53.82

**CE Diameter STDV ( $\mu\text{m}$ ):** 7.40

**Particles Counted:** 4679

**CE Diameter RSD (%):** 191.78

Volume transformation: CE Diameter ( $\mu\text{m}$ ) smoothed over 11 points



Record 588: Vinnapas 7055E

## Comments:

Morphologi

Malvern Instruments Worldwide

[www.malvern.com](http://www.malvern.com)