

HS Circularity - Number Distribution



Measurement Details

Sample Name: FILLITE EGP5

SOP Name: MATERIE PRIME.vsop

User Name: morphologi

Date: 06 May 2014 10:22:51

Edited: False

Edited On: 06 May 2014 10:22:51

Analysis

SOP Analysis: 3.0

SOP Fill Holes: True

SOP Segmentation: None

SOP Trash Size: 10

SOP Optic(s) used: 2.5x

Result

HS Circularity Minimum: 0.018

HS Circularity D[n, 0.1]: 0.652

HS Circularity Maximum: 1.000

HS Circularity D[n, 0.5]: 0.863


HS Circularity Mean: 0.840

HS Circularity D[n, 0.9]: 0.958

Particles Counted: 286317

HS Circularity STDV: 0.135

HS Circularity RSD (%): 16.040



Comments:

Morphologi

Malvern Instruments Worldwide

www.malvern.com