

Doping Stability Report -- Fe in NaCoO₂ at 200 C

Generated: 2026-05-29 21:04 Host: NaCoO₂ Dopant: Fe

Executive Summary

Fe preferentially occupies the Co layer. The formation energy difference between the two layers is +6.368 eV, strongly favouring the Co site. MD confirms this preference: on the Co site the dopant MSD plateau slope is -0.00080 Å²/ps (stable), compared to -0.00009 Å²/ps on the Na site. The Co-site result is isovalent (no charge mismatch), so the formation energy is fully reliable. The Na-site E_f is approximate due to a charge surplus of +2 that cannot be modelled in CHGNet.

Site	E _f (eV)	Charge	Compensation	MSD pass	Coord pass	Verdict
Co	-0.511	+0	No	PASS	PASS	STABLE
Na	+5.857	+2	Yes	PASS	FAIL	STRUCTURAL COLLAPSE

Fe at the Co layer -- STABLE

Charge situation

Fe replaces Co with no change in oxidation state (isovalent substitution, charge mismatch = 0). No charge compensation is needed. The formation energy is fully reliable.

Formation Energy (thermodynamic stability)

Formation energy E _f	-0.5109 eV	PASS	< 1.0 eV to pass
---------------------------------	-------------------	-------------	------------------

E_f = -0.511 eV. This value is slightly negative, indicating that Fe incorporation is thermodynamically favorable at the Co site.

Molecular Dynamics Stability (200 C, 25 ps)

MSD slope (late-time)	-0.00080 Å²/ps	PASS	< 0.005 to pass (plateau = stable)
Final MSD	0.105 Å²	----	
Max displacement	0.716 Å	----	
Coordination (min/mean/max)	6 / 6.0 / 6	PASS	relaxed = 6, tolerance +/-1
Mean bond length (MD vs relaxed)	2.025 Å (relaxed: 2.0)	----	
Lattice volume change	+0.00 %	PASS	< +/-5% to pass

Late-time MSD slope = -0.00080 Å²/ps. The negative slope is a flat plateau -- essentially no migration detected. Final MSD = 0.105 Å²; maximum displacement from starting position = 0.72 Å.

Coordination was exactly 6 throughout the entire trajectory -- a near-perfect result indicating the dopant held its local environment rigidly. Mean nearest-neighbour distance during MD = 2.025 Å.

Volume change = +0.00%. The host lattice is mechanically intact.

VERDICT: STABLE

Fe is thermodynamically favorable and kinetically stable on the Co site at 200 C. All four stability criteria

Doping Stability Report -- Fe in NaCoO₂ at 200 C

pass: formation energy is favorable, the dopant does not migrate during MD, its coordination environment is preserved, and the host lattice volume is unchanged.

Fe at the Na layer -- STRUCTURAL COLLAPSE

Charge situation

Fe replaces Na with a charge surplus of +2. CHGNet cannot model this compensation (would require Co oxidation or electron addition). The formation energy below is approximate.

Formation Energy (thermodynamic stability)

Formation energy E_f	+5.8567 eV	FAIL	< 1.0 eV to pass
------------------------	-------------------	-------------	------------------

E_f = +5.857 eV (approximate -- charge surplus not modelled in CHGNet). This value is large and positive, indicating that Fe incorporation is thermodynamically unfavorable under equilibrium conditions at the Na site.

Molecular Dynamics Stability (200 C, 25 ps)

MSD slope (late-time)	-0.00009 A²/ps	PASS	< 0.005 to pass (plateau = stable)
Final MSD	0.948 A²	----	
Max displacement	1.036 A	----	
Coordination (min/mean/max)	4 / 5.8 / 7	FAIL	relaxed = 6, tolerance +/-1
Mean bond length (MD vs relaxed)	2.172 A (relaxed: 2.1)	----	
Lattice volume change	+0.00 %	PASS	< +/-5% to pass

Late-time MSD slope = -0.00009 A²/ps. The negative slope is a flat plateau -- essentially no migration detected. Final MSD = 0.948 A²; maximum displacement from starting position = 1.04 A.

Coordination fluctuated between 4 and 7 (mean 5.8), deviating by more than +/-1 from the relaxed value (6). This may indicate structural distortion, or that the bond-length cutoff is too close to the actual bond length -- check the `coordination_cutoff_A` setting. Mean nearest-neighbour distance during MD = 2.172 A.

Volume change = +0.00%. The host lattice is mechanically intact.

VERDICT: STRUCTURAL COLLAPSE

The coordination criterion failed while MSD and volume both pass, suggesting a possible cutoff artifact rather than a true structural collapse. The Fe atom barely moves (MSD = 0.948 A²) but the coordination count fluctuates because the bond length at the Na site is close to the analysis cutoff. Consider increasing `coordination_cutoff_A` and re-running analysis.

Site Preference Comparison

The Co site is preferred by 6.368 eV over the Na site. Formation energy: -0.511 eV (Co) vs +5.857 eV (Na). Fe preferentially occupies the Co layer. The formation energy difference between the two layers is +6.368 eV, strongly favouring the Co site. MD confirms this preference: on the Co site the dopant MSD plateau slope is -0.00080 A²/ps (stable), compared to -0.00009 A²/ps on the Na site. The Co-site result is isovalent (no charge mismatch), so the formation energy is fully reliable. The Na-site E_f is approximate

due to a charge surplus of +2 that cannot be modelled in CHGNet.

Caveats and Limitations

? CHGNet is charge-neutral.

The potential does not model oxidation states, polaron formation, or electron/hole localisation. Formation energies for aliovalent dopants (charge mismatch $\neq 0$) are approximate even when structural compensation defects are included.

? No Freysoldt/Kumagai correction.

Electrostatic finite-size corrections for charged defects require the host dielectric tensor and the DFT electrostatic potential, neither of which is available from a neural-network potential. For publication-quality E_f of charged defects, follow up with DFT using doped or pymatgen-analysis-defects.

? Metal-rich reference state.

Chemical potentials are computed from elemental ground-state structures. Synthesis under oxide-rich or other conditions shifts all E_f values by additive constants; the relative ordering of sites is unaffected.

? MD timescales are short (25 ps default).

This is sufficient to assess local site stability and rapid migration, but cannot resolve slow diffusion mechanisms. A non-plateauing MSD confirms instability; a plateau does not guarantee stability on longer timescales.

? Energy rankings are more trustworthy than absolute values.

CHGNet is a universal MLIP trained on r2SCAN DFT. Formation-energy errors for transition-metal oxides are typically 50-150 meV/atom. Use relative orderings (which site is preferred?) as the primary result.