

Doping Stability Report -- Mn in NaCoO2 at 200 C

Generated: 2026-05-30 09:53 Host: NaCoO2 Dopant: Mn

Executive Summary

Mn preferentially occupies the Co layer. The formation energy difference between the two layers is +6.621 eV, strongly favouring the Co site. MD confirms this preference: on the Co site the dopant MSD plateau slope is 0.00018 A²/ps (stable), compared to 0.00168 A²/ps on the Na site. The Co-site result is isovalent (no charge mismatch), so the formation energy is fully reliable. The Na-site E_f is approximate due to a charge surplus of +2 that cannot be modelled in CHGNet.

Site	E _f (eV)	Charge	Compensation	MSD pass	Coord pass	Verdict
Co	-2.098	+0	No	PASS	PASS	STABLE
Na	+4.523	+2	Yes	PASS	FAIL	STRUCTURAL COLLAPSE

Mn at the Co layer -- STABLE

Charge situation

Mn replaces Co with no change in oxidation state (isovalent substitution, charge mismatch = 0). No charge compensation is needed. The formation energy is fully reliable.

Formation Energy (thermodynamic stability)

Formation energy E _f	-2.0981 eV	PASS	< 1.0 eV to pass
---------------------------------	------------	------	------------------

E_f = -2.098 eV. This value is strongly negative, indicating that Mn incorporation is thermodynamically very favorable at the Co site.

Molecular Dynamics Stability (200 C, 25 ps)

MSD slope (late-time)	0.00018 A ² /ps	PASS	< 0.005 to pass (plateau = stable)
Final MSD	0.045 A ²	----	
Max displacement	0.901 A	----	
Coordination (min/mean/max)	6 / 6.0 / 6	PASS	relaxed = 6, tolerance +/-1
Mean bond length (MD vs relaxed)	1.936 A (relaxed: 1.9)	----	
Lattice volume change	+0.00 %	PASS	< +/-5% to pass

Late-time MSD slope = 0.00018 A²/ps. The slope is near zero, confirming the dopant is tightly confined to its site. Final MSD = 0.045 A²; maximum displacement from starting position = 0.90 A.

Coordination was exactly 6 throughout the entire trajectory -- a near-perfect result indicating the dopant held its local environment rigidly. Mean nearest-neighbour distance during MD = 1.936 A.

Volume change = +0.00%. The host lattice is mechanically intact.

VERDICT: STABLE

Mn is thermodynamically favorable and kinetically stable on the Co site at 200 C. All four stability criteria

Doping Stability Report -- Mn in NaCoO₂ at 200 C

pass: formation energy is favorable, the dopant does not migrate during MD, its coordination environment is preserved, and the host lattice volume is unchanged.

Mn at the Na layer -- STRUCTURAL COLLAPSE

Charge situation

Mn replaces Na with a charge surplus of +2. CHGNet cannot model this compensation (would require Co oxidation or electron addition). The formation energy below is approximate.

Formation Energy (thermodynamic stability)

Formation energy E_f	+4.5229 eV	FAIL	< 1.0 eV to pass
------------------------	-------------------	-------------	------------------

E_f = +4.523 eV (approximate -- charge surplus not modelled in CHGNet). This value is large and positive, indicating that Mn incorporation is thermodynamically unfavorable under equilibrium conditions at the Na site.

Molecular Dynamics Stability (200 C, 25 ps)

MSD slope (late-time)	0.00168 Å²/ps	PASS	< 0.005 to pass (plateau = stable)
Final MSD	0.268 Å²	----	
Max displacement	0.973 Å	----	
Coordination (min/mean/max)	4 / 5.9 / 7	FAIL	relaxed = 6, tolerance +/-1
Mean bond length (MD vs relaxed)	2.195 Å (relaxed: 2.2)	----	
Lattice volume change	+0.00 %	PASS	< +/-5% to pass

Late-time MSD slope = 0.00168 Å²/ps. The slope is small and below the migration threshold -- the dopant is site-stable. Final MSD = 0.268 Å²; maximum displacement from starting position = 0.97 Å.

Coordination fluctuated between 4 and 7 (mean 5.9), deviating by more than +/-1 from the relaxed value (6). This may indicate structural distortion, or that the bond-length cutoff is too close to the actual bond length -- check the coordination_cutoff_A setting. Mean nearest-neighbour distance during MD = 2.195 Å.

Volume change = +0.00%. The host lattice is mechanically intact.

VERDICT: STRUCTURAL COLLAPSE

The coordination criterion failed while MSD and volume both pass, suggesting a possible cutoff artifact rather than a true structural collapse. The Mn atom barely moves (MSD = 0.268 Å²) but the coordination count fluctuates because the bond length at the Na site is close to the analysis cutoff. Consider increasing coordination_cutoff_A and re-running analysis.

Site Preference Comparison

The Co site is preferred by 6.621 eV over the Na site. Formation energy: -2.098 eV (Co) vs +4.523 eV (Na). Mn preferentially occupies the Co layer. The formation energy difference between the two layers is +6.621 eV, strongly favouring the Co site. MD confirms this preference: on the Co site the dopant MSD plateau slope is 0.00018 Å²/ps (stable), compared to 0.00168 Å²/ps on the Na site. The Co-site result is isovalent (no charge mismatch), so the formation energy is fully reliable. The Na-site E_f is approximate

due to a charge surplus of +2 that cannot be modelled in CHGNet.

Caveats and Limitations

? CHGNet is charge-neutral.

The potential does not model oxidation states, polaron formation, or electron/hole localisation. Formation energies for aliovalent dopants (charge mismatch $\neq 0$) are approximate even when structural compensation defects are included.

? No Freysoldt/Kumagai correction.

Electrostatic finite-size corrections for charged defects require the host dielectric tensor and the DFT electrostatic potential, neither of which is available from a neural-network potential. For publication-quality E_f of charged defects, follow up with DFT using doped or pymatgen-analysis-defects.

? Metal-rich reference state.

Chemical potentials are computed from elemental ground-state structures. Synthesis under oxide-rich or other conditions shifts all E_f values by additive constants; the relative ordering of sites is unaffected.

? MD timescales are short (25 ps default).

This is sufficient to assess local site stability and rapid migration, but cannot resolve slow diffusion mechanisms. A non-plateauing MSD confirms instability; a plateau does not guarantee stability on longer timescales.

? Energy rankings are more trustworthy than absolute values.

CHGNet is a universal MLIP trained on r2SCAN DFT. Formation-energy errors for transition-metal oxides are typically 50-150 meV/atom. Use relative orderings (which site is preferred?) as the primary result.