

Doping Stability Report -- Fe in NaCoO2 at 300 C

Generated: 2026-05-30 03:39 Host: NaCoO2 Dopant: Fe

Executive Summary

Fe preferentially occupies the Co layer. The formation energy difference between the two layers is +6.368 eV, strongly favouring the Co site. MD confirms this preference: on the Co site the dopant MSD plateau slope is 0.00690 Å²/ps (stable), compared to 0.00688 Å²/ps on the Na site. The Co-site result is isovalent (no charge mismatch), so the formation energy is fully reliable. The Na-site E_f is approximate due to a charge surplus of +2 that cannot be modelled in CHGNet.

Site	E _f (eV)	Charge	Compensation	MSD pass	Coord pass	Verdict
Co	-0.511	+0	No	FAIL	PASS	MIGRATION (favorable site but
Na	+5.857	+2	Yes	FAIL	FAIL	UNSTABLE (migration + structu

Fe at the Co layer -- MIGRATION (favorable site but dopant relocates during MD)

Charge situation

Fe replaces Co with no change in oxidation state (isovalent substitution, charge mismatch = 0). No charge compensation is needed. The formation energy is fully reliable.

Formation Energy (thermodynamic stability)

Formation energy E _f	-0.5109 eV	PASS	< 1.0 eV to pass
---------------------------------	------------	------	------------------

E_f = -0.511 eV. This value is slightly negative, indicating that Fe incorporation is thermodynamically favorable at the Co site.

Molecular Dynamics Stability (300 C, 25 ps)

MSD slope (late-time)	0.00690 Å ² /ps	FAIL	< 0.005 to pass (plateau = stable)
Final MSD	0.380 Å ²	----	
Max displacement	0.905 Å	----	
Coordination (min/mean/max)	6 / 6.0 / 7	PASS	relaxed = 6, tolerance +/-1
Mean bond length (MD vs relaxed)	2.027 Å (relaxed: 2.0)	----	
Lattice volume change	+0.00 %	PASS	< +/-5% to pass

Late-time MSD slope = 0.00690 Å²/ps. The slope exceeds the plateau threshold, suggesting mild drift or site-hopping. Final MSD = 0.380 Å²; maximum displacement from starting position = 0.90 Å.

Coordination fluctuated between 6 and 7 (mean 6.0), within the +/-1 tolerance of the relaxed value (6). This is consistent with normal thermal vibration. Mean nearest-neighbour distance during MD = 2.027 Å.

Volume change = +0.00%. The host lattice is mechanically intact.

VERDICT: MIGRATION (favorable site but dopant relocates during MD)

The formation energy is favorable but Fe migrates away from the Co site during MD. The relaxed structure

is not the true resting site. Inspect the MSD and trajectory to identify where the dopant ends up.

Fe at the Na layer -- UNSTABLE (migration + structural distortion)

Charge situation

Fe replaces Na with a charge surplus of +2. CHGNet cannot model this compensation (would require Co oxidation or electron addition). The formation energy below is approximate.

Formation Energy (thermodynamic stability)

Formation energy E_f	+5.8567 eV	FAIL	< 1.0 eV to pass
------------------------	-------------------	-------------	------------------

E_f = +5.857 eV (approximate -- charge surplus not modelled in CHGNet). This value is large and positive, indicating that Fe incorporation is thermodynamically unfavorable under equilibrium conditions at the Na site.

Molecular Dynamics Stability (300 C, 25 ps)

MSD slope (late-time)	0.00688 Å²/ps	FAIL	< 0.005 to pass (plateau = stable)
Final MSD	3.236 Å²	----	
Max displacement	2.004 Å	----	
Coordination (min/mean/max)	4 / 5.8 / 7	FAIL	relaxed = 6, tolerance +/-1
Mean bond length (MD vs relaxed)	2.166 Å (relaxed: 2.1)	----	
Lattice volume change	+0.00 %	PASS	< +/-5% to pass

Late-time MSD slope = 0.00688 Å²/ps. The slope exceeds the plateau threshold, suggesting mild drift or site-hopping. Final MSD = 3.236 Å²; maximum displacement from starting position = 2.00 Å.

Coordination fluctuated between 4 and 7 (mean 5.8), deviating by more than +/-1 from the relaxed value (6). This may indicate structural distortion, or that the bond-length cutoff is too close to the actual bond length -- check the coordination_cutoff_A setting. Mean nearest-neighbour distance during MD = 2.166 Å.

Volume change = +0.00%. The host lattice is mechanically intact.

VERDICT: UNSTABLE (migration + structural distortion)

Verdict: UNSTABLE (migration + structural distortion). Refer to the individual criteria above.

Site Preference Comparison

The Co site is preferred by 6.368 eV over the Na site. Formation energy: -0.511 eV (Co) vs +5.857 eV (Na). Fe preferentially occupies the Co layer. The formation energy difference between the two layers is +6.368 eV, strongly favouring the Co site. MD confirms this preference: on the Co site the dopant MSD plateau slope is 0.00690 Å²/ps (stable), compared to 0.00688 Å²/ps on the Na site. The Co-site result is isovalent (no charge mismatch), so the formation energy is fully reliable. The Na-site E_f is approximate due to a charge surplus of +2 that cannot be modelled in CHGNet.

Caveats and Limitations

? CHGNet is charge-neutral.

Doping Stability Report -- Fe in NaCoO₂ at 300 C

The potential does not model oxidation states, polaron formation, or electron/hole localisation. Formation energies for aliovalent dopants (charge mismatch $\neq 0$) are approximate even when structural compensation defects are included.

? No Freysoldt/Kumagai correction.

Electrostatic finite-size corrections for charged defects require the host dielectric tensor and the DFT electrostatic potential, neither of which is available from a neural-network potential. For publication-quality E_f of charged defects, follow up with DFT using doped or pymatgen-analysis-defects.

? Metal-rich reference state.

Chemical potentials are computed from elemental ground-state structures. Synthesis under oxide-rich or other conditions shifts all E_f values by additive constants; the relative ordering of sites is unaffected.

? MD timescales are short (25 ps default).

This is sufficient to assess local site stability and rapid migration, but cannot resolve slow diffusion mechanisms. A non-plateauing MSD confirms instability; a plateau does not guarantee stability on longer timescales.

? Energy rankings are more trustworthy than absolute values.

CHGNet is a universal MLIP trained on r2SCAN DFT. Formation-energy errors for transition-metal oxides are typically 50-150 meV/atom. Use relative orderings (which site is preferred?) as the primary result.