Garlock
SEALING TECHNOLOGIES®

an EnPro Industries company

Garlock 7986

MATERIAL PROPERTIES[*]

Color:	Black
Composition:	Neoprene rubber
Durometer, Shore A, +/- 5:	60
Temperature[2], °F (°C)	
Minimum:	-20 (-29)
Maximum:	+250 (+121)
Pressure[2], Maximum, psig (bar):	250 (17)
P x T (max.)[2], psig x °F (bar x °C):	20,000 (600)
Finish Available	
Thru 1/8":	Cloth
Over 1/8":	Smooth
Meets Specification:	MIL-R-3065 and MIL-Std. 417 Type S Grade SC620 A1 E3 E5

PHYSICAL PROPERTIES[*]

ASTM D412	**Tensile Strength**, psi (N/mm^2):	2000 (14)
ASTM D412	**Elongation**, %:	350
ASTM D395 B	**Compression Set**, 25% Deflection, Max. %	
	70 hours at 212°F (100°C):	35
ASTM D149	**Dielectric Properties**, range, volts/mil.	
	Sample conditioning	1/8"
	None	118
ASTM F586	**Design Factors**	
	"m" factor:	0.50
	"y" factor, psi (N/mm^2):	0[3]
ASTM D2000	**Line Call Out**:	6BC620E014E034G21

IMMERSION PROPERTIES[*]

ASTM D471	**Volume Change in ASTM #1 Oil**, Range %	
	70 hours at 212°F (100°C):	-4 to 3
ASTM D471	**Volume Change in ASTM #3 Oil**, Range %	
	70 hours at 212°F (100°C):	50 to 80

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material.

* Values do not constitute specification Limits

2 When approaching the maximum or minimum ratings consult Garlock Applications Engineering

3 Garlock Applications Engineering has historically recommended a suggested "Y" value of 100psi (0.7N/mm^2) for these elastomers.

1611666 Division Street • Palmyra, New York 14522 USA • 1-315-597-4811 • Toll Free: 1-800-448-6688 • Fax: 1-315-597-3216 • www.garlock.com