

Garlock 2400

MATERIAL PROPERTIES*

Color:	Gray
Composition:	Aramid and inorganic fibers with a nitrile binder.
	Anti-stick contains PTFE on this style.
Fluid Services¹:	Water, aliphatic hydrocarbons, oils, gasoline and saturated steam ⁴
Temperature², °F (°C)	
Minimum:	-100 (-73)
Continuous Max:	+400 (+205)
Maximum:	+700 (+371)
Pressure², Maximum, psig (bar):	1000 (70)
P x T (max.)², psig x °F (bar x °C)	
1/32 and 1/16":	350,000 (12,000)
1/8":	250,000 (8,600)

PHYSICAL PROPERTIES*

ASTM F36	Compressibility , range, %:	10-20
ASTM F36	Recovery , %:	50
ASTM F38	Creep Relaxation , %:	20
ASTM F152	Tensile , Across Grain, psi (N/mm ²):	1750 (12)
ASTM F1315	Density , lbs./ft. ³ (grams/cm ³):	98 (1.57)
ASTM D149	Dielectric Properties , range, volts/mil.	
	Sample conditioning	<u>1/16"</u> <u>1/8"</u>
	3 hours at 250°F:	475 ⁽³⁾ 298 ⁽³⁾
	96 hours at 100% Relative Humidity:	- -

SEALING CHARACTERISTICS*

	ASTM F37B Fuel A	ASTM F37B Nitrogen
Gasket Load , psi (N/mm ²):	500 (3.5)	3000 (20.7)
Internal Pressure , psig (bar):	9.8 (0.7)	30 (2)
Leakage	1.0 ml/hr.	1.5 ml/hr.

IMMERSION PROPERTIES* - ASTM F146 Fluid Resistance after Five Hours

	ASTM #1 Oil 300°F (150°C)	ASTM IRM #903 300°F (150°C)	ASTM Fuel A 70-85°F (20-30°C)	ASTM Fuel B 70-85°F (20-30°C)
Thickness Increase , (%)	0-10	0-15	0-10	0-10
Weight Increase , (%)	<15	-	<10	<15
Tensile Loss , (%)	-	<35	-	-

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-11 properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

* Values do not constitute specification Limits

¹ See Garlock chemical resistance guide.

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering. Minimum temperature rating is conservative.

³ Indicates current arced around and not through gasket. Dielectric higher than indicated.